
















	Standard	Result
 Size		1500 x 250 mm
 Thickness		4.5 mm
 Wear Layer		0.5 mm
Backing		PVC Friction Pad
K-Guard Plus		Yes
Box quantity		8 Planks / 3.00 m ²
Warranty	Commercial	15 years wear*
	Residential	Lifetime wear*
Bevelled Edge		No
Standards	EN 649	Pass
	ASTM F1700	Pass
 Classification		Commercial Heavy Duty use Domestic Extra Heavy Duty use
 Staining Resistance	EN 423	Class 0
	ASTM F925	Pass
 Colour Fastness to Light	ISO 105-B02	≥7
	ASTM F1515	<8
 Abrasion Resistance	EN 660-2	Group T
	ASTM D3884	Pass
 Dimensional stability	EN 434	≤ 0.10%
	ASTM F2199	Pass
 Acoustic Impact noise reduction	NCC 2016 F5.3 (a) result refer to Karndean INSUL Marshall Day Software report for your MULTI Res specification including AAAC Star rating	
	ISO 140-8 Improved Impact Sound Insulation	ΔL _w = 14dB
	ASTM E492-09 Impact Insulation Class	IIC 56dB
	Suitable for use on upper floors of residential high-rise apartment buildings without the need for a separate acoustic underlay under certain build specifications - precise details available from Karndean.	
 Electrical behaviour body voltage	EN 1815	Pass
	AATCC 134-1996	Pass
 Indentation - residual	EN 433	≤ 0.1mm
	ASTM F1914	<8%
 Castor chair continuous use	EN 425	Pass
 Thermal resistance	ISO 8302	0.0245 m ² K/W Suitable for underfloor heating
 Reaction to Fire	AS/NZS ISO 9239.1:2003	CRF: Plank 8.0 kW/m ² Smoke value: 105% min
 Slip resistance**	AS/NZS 4586:2013	R10
Adhesive		Karndean Hi-Tack PS Adhesive when applicable. Please refer to Installation Guidelines.
Recycling		Suitable
Environmental	Floorscore (SCS-EC10.2-2007)	Indoor air quality certified; Compliant low emitting VOC emissions.

*Subject to terms

**Slip resistance is measured on ex-factory product. Slip resistance in use will be affected by surface contamination and by how the product is maintained

For more information:

Australia
Call: 1800 33 11 70
Email: customerservice@karndean.com.au
Visit: www.karndean.com

New Zealand
Call: 0800 44 21 01
Email: customerservice@karndean.co.nz
Visit: www.karndean.com